

|                     |      |     |
|---------------------|------|-----|
| CI/SfB              | (43) | Vv5 |
| CAW M60             |      |     |
| Uniclass L538:P7103 |      |     |
| December 2009       |      |     |

# CS933 Surefoot

## Anti-Slip Epoxy Coating

### KEY BENEFITS SUMMARY

- Solvent free
- Lightly textured to provide anti-slip surface

### PRODUCT INFORMATION

#### Description

Tremco CS933 Surefoot is a solvent free, lightly textured epoxy resin with a pre-dispersed aggregate.

#### Typical Uses

Factories, warehouses and other industrial facilities where anti-slip properties are required.

#### Packaging

10 kg (2 component kit)

#### Colours

Tile Red, Light Grey, Mid Grey and Mid Blue. Wherever possible ensure that a single batch number is used for topcoat to avoid colour variation.

#### Coverage Rate

Up to 6 to 8 m<sup>2</sup> per litre unit

#### Cure Time

Working time: Approx 30 minutes  
Full traffic: 24 hours

#### Storage

Store in dry shaded conditions between +5°C and +25°C.



#### Shelf Life

12 months when stored as recommended in original unopened packaging.

#### Health & Safety Precautions

Product Health and Safety Data Sheets must be read and understood before use.

### USAGE GUIDELINES

#### Standards

All aspects of the installation must be in accordance with the requirements of BS8204, BS8203 (Installation of Resilient floorcoverings) or BS5325 (Installation of Textile floorcoverings) and supplementary specifications.

#### Preparation

Subfloor preparation is highly important with products of this nature. The surface should be free of oil and grease. Weak material or laitence should be removed prior to application of the product. Highly polished surfaces e.g. powerfloated concrete, marble and terrazzo tiles should be mechanically textured. The floor should then be either vacuumed or swept clean. Sound, stable floor construction is essential.

# TREMCO

# CS933 Surefoot

Tremco illbruck Limited  
Coupland Road  
Hindley Green, Wigan WN2 4HT UK  
Tel: 01942 251400  
Fax: 01942 251410  
Email: uk.info@tremco-illbruck.com  
Website: www.tremco-illbruck.co.uk

## Mixing

Mix the two liquid components of the Tremco CS933 Surefoot using a slow speed drill and stirrer attachment, spatula or other square edged implement. Mix full kits only - do not attempt to split packs.

**IMPORTANT:** Mixed sealer should not be left in the tin as exothermic action will produce flash set in 10-15 minutes.

## Application

Apply by roller. Two coats are usually required - the second coat should not be applied until the first coat has cured.

The minimum application temperature is 5 °C although please note that curing times will be significantly extended. Under certain drying conditions below 10 °C there is a risk of blooming.

## Technical Service

Tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

## Guarantee / Warranty

Tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco illbruck written instructions and (b) in any application recommended by Tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

Tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.